

## VINYLIA BTM (S)

## 乙烯漆 (S)

PRODUCT DESCRIPTION 产品简介	General anticorrosive primer based on vinyl resin with resisting pigments. 由乙烯树脂和防腐颜料组成的防腐底漆。	
RECOMMENDED USE 用途	For steel structure in immersion and non immersion areas.such as ship bottop, boottops 用于浸没和非浸没区域的钢结构表面，如船底，水线部位等。	
FEATURES 产品特性	<p>Excellent corrosion resistance 极好的防腐性能</p> <p>Very good adhesion to various substrates 同各类底材附着力良好</p> <p>Quick drying 干燥迅速</p> <p>Excellent resistance to sea water and cathodic protection 优良的耐海水性和阴极保护能力</p> <p>Can be overcoated with both chlorinated rubber and oleoresinous topcoats and various antifouling paints 可以覆涂氯化橡胶、油性涂料或其它各类防污涂料</p> <p>Tar free 不含焦油</p>	
PHYSICAL PROPERTIES 基本数据		
Color 颜色	Silver brown and Brown 银棕色、棕色	
Volume Solids 体积固体份	40%	
VOC 挥发性有机化合物含量	570g/L 570g/L	
Flash Point 闪点	Greater than 15℃ 15℃以上	
Film thickness 涂装膜厚	Dry : 40–80 microns/coat 干膜: 40–80微米/道	Wet : 100–200microns/coat 湿膜: 100–200微米/道
Theoretical Coverage 理论涂布率	<p>8.0 m<sup>2</sup>/Ltr/50 microns 8.0平方米/升/50 μm</p> <p>Practical coverage depending on surface conditions, environment, applications, etc. 实际涂布率与表面处理, 外界环境, 施工方法等多种因素有关。</p>	
APPLICATION 施工		
Application Temperature 施工温度	-5℃–40℃	
Mixing 混合	Mix thoroughly with power agitator 使用动力工具搅拌均匀	



Mixing Ratio  
混合比例

One component coating  
单组份涂料

Application Methods  
施工方法

Airless spray, air spray, brush and roller  
无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm
Nozzle pressure	出口压力	≥10Mpa
Thinning ratio	稀释比率	0-10% by volume (体积比)

Brush/Roller 刷涂、滚涂

Thinning ratio	稀释比率	0-10% by volume (体积比)
----------------	------	-----------------------

Thinner  
稀释剂

Vinylia Thinner  
乙烯稀释剂

Drying time &  
Overcoating interval  
干燥时间&涂装间隔

Temperature	温度	-5℃	5℃	20℃	30℃
Surface dry	指触干燥	1.5hrs	1hr	30mins	15mins
Touch dry	半硬干燥	10hrs	6hrs	4hrs	3hrs
Min. interval	最小涂装间隔	10hrs	6hrs	4hrs	3hrs
Max. interval	最大涂装间隔	—	—	—	—

Applied Substrates  
适用底材

Bare steel  
裸钢

Typical topcoat  
适用上涂

Rabamarine BTB, or according to the coating systems of Cosco Kansai.  
Rabamarine BTB,或参考我司推荐配套。

STORAGE  
贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.  
贮存于干燥阴凉的环境中, 远离热源及火源。包装桶必须保持封闭。

Shelf life  
贮存期限

12months from date of production (25℃)  
自生产之日起12个月 (25℃)

DISCLAIMER  
提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this data sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 本说明书的内容也会随时进行更改, 此中所有信息均以我方确认为主。产品使用前, 请确认所持说明书为最新版本。

REMARKS  
备注

Drying time before flooding should be more than 16hours(20℃)  
耐浸干燥时间需超过16小时(20℃)